



FABRIC SPECIFICATION SHEET

Style		FM2
Construction		Polypropylene scrim reinforced needlefelt
Colour		white
Weight	g/m ²	500
Thickness	mm	1.7
Air Permeability	cc/cm ² /sec @ 12.7 mm H ₂ O	14
Scrim		Staple fibre
Max. Lineal Shrinkage	For 90 min @ 80°C	3%
Fibre		Polypropylene
Bursting Strength	kg/cm ²	50
Tensile Strength	kg/5 cm width	MD 120 CD 160
Surface Treatment		Heat Set
Finish		Calendered
Max. Operating Temperature	°C	80
Application		Excellent chemical resistance Excellent hydrolysis resistance

FM2

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven, Auckland, New Zealand
Ph: (09)483-7149 Fax: (09)483-4355
Email: akld@filtercorp.co.nz

152 Hazeldean Road
Addington, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.co.nz

Web site: <http://www.filtercorp.co.nz>