



FABRIC SPECIFICATION SHEET

Style		FM35
Construction		Homopolymer Acrylic
Colour		Yellow
Weight	g/m ²	500
Thickness	mm	2.0
Air Permeability	cc/cm ² /sec @ 12.7 mm H ₂ O	18
Scrim		Staple fibre
Max. Linial Shrinkage	For 120 min @ 125° C	3%
Fibre		Homo Acrylic
Bursting Strength	kg/cm ²	30
Tensile Strength	kg/5 cm width	MD 60 CD 70
Surface Treatment		Singed
Finish		Heat set
Max. Operating Temperature	°C	125
Application		Excellent acid resistance Excellent hydrolysis resistance

FM35

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven, Auckland, New Zealand
Ph: (09)483-7149 Fax: (09)483-4355
Email: akld@filtercorp.co.nz

152 Hazeldean Road
Addington, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.co.nz

Web site: <http://www.filtercorp.co.nz>