



FABRIC SPECIFICATION SHEET

MDF400E

Style	MDF400E	
Construction	Polyester multifilament scrim supported needlefelt, antistatic	
Colour	White	
Weight	g/m ²	400 ± 20
Thickness	mm	1.7 ± 10%
Air Permeability	dm ³ /dm ² /min @ 20mm H ₂ O	139
Max. Linial Shrinkage	For 240 min @ 170 °C	2.99%
Fibre	97% Virgin Polyester 3% Electrostatic Carbon string lines	
Bursting Strength	kg/cm ²	52+
Surface Treatment	Superglaze one side	
Finish	Heat set and signed one side.	
Max. Operating Temperature	°C	130
Application	Anti-static needlefelt for reverse-pulse dust collectors	

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven 0749, Auckland, New Zealand
Ph: (09)481-9999 Fax: (09)483-4355
Email: akld@filtercorp.biz

152 Hazeldean Road
Addington 8024, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.biz

Web site: <http://www.filtercorp.biz>